

12

EUROPEAN PATENT APPLICATION

21 Application number: 88304830.8

51 Int. Cl.⁴: **H01M 4/42 , H01M 4/32 ,
H01M 10/30**

22 Date of filing: 27.05.88

30 Priority: 11.04.88 JP 88416/88

43 Date of publication of application:
18.10.89 Bulletin 89/42

64 Designated Contracting States:
DE FR GB

71 Applicant: **YUASA BATTERY COMPANY
LIMITED**
6-6, Johsai-cho
Takatsuki-City Osaka Prefecture(JP)

72 Inventor: Oshitani, Masahiko
Yuasa Battery Company Limited 6-6,
Johsai-cho
Takatsuki City Osaka Prefecture(JP)
Inventor: Yufu, Hiroshi
Yuasa Battery Company Limited 6-6,
Johsai-cho
Takatsuki City Osaka Prefecture(JP)

74 Representative: **Hartley, David et al**
c/o Withers & Rogers 4 Dyer's Buildings
Holborn
London, EC1N 2JT(GB)

54 **Nickel electrode for alkaline battery and battery using said nickel electrode.**

57 A nickel electrode using a porous alkali-proof metal fiber substrate as a current collector and a nickel hydroxide powder as a principal component of active material is precluded from formation of the higher oxide, γ -NiOOH, improved in the ratio of utilization of the active material, and enabled to enjoy high energy density and long service life when the nickel hydroxide powder employed therein is of a specific type possessing a pore radius in the range of 15 to 30 Å, a total pore volume of not more than 0.05 ml/g, and a specific surface area in the range of 15 to 30 m²/g. An alkaline battery is also provided by the invention which uses the nickel electrode described above.

EP 0 337 029 A2

NICKEL ELECTRODE FOR ALKALINE BATTERY AND BATTERY USING SAID NICKEL ELECTRODE

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

This invention relates to a nickel electrode for use in an alkaline battery and to a battery using this nickel electrode.

DESCRIPTION OF THE PRIOR ART

The nickel electrodes heretofore used generally in alkaline batteries are designated as sintered electrodes. The porous substrate is prepared by sintering nickel powder on the perforated steel sheet. The process by which the porous substrate is filled with active material is called impregnation. The impregnation is accomplished by means of four steps carried out in sequence, namely, soaking the substrate in a nitrate solution, converting into hydroxide in alkaline solution, rinsing with water, and drying. This four-process is repeated until the desired amount of active material is obtained.

This impregnating method, however, is highly complicated because many inevitable repetitions of one treatment. This complication of procedure constitutes itself one factor for an addition to the cost of the product. Moreover, since the porosity of the substrate is limited by practical reason to the maximum of 80% and consequently the loading density of active material is very low, batteries are produced by this method with as low a maximum energy density as 400 mAh/cc at the best.

Non-sintered electrodes have been widely developed. For example, as disclosed in Japanese Patent Application Disclosure SHO 56(1981)-59460, the electrode is produced by mixing twenty-odd % by weight of graphite powder as a conductive additive with nickel hydroxide powder coated with cobalt hydroxide, extruding the mixture into a strip and then laminating two layers of this strip to the both sides of a nickel plate which is a current collector. Thus produced electrode requires a large amount of graphite which is the conductive additive, just like a pocket-type electrode. The conductive additive contributes nothing to the volume of the electrode so that it makes the volumetric density of the electrode lowered and produces a large amount of carbonate due to decomposition of graphite. Therefore, the conductive additive can not be used for the battery such as sealed nickel-cadmium battery which contains a small amount of electrolyte.

As one solution of this drawback, for example, pasted nickel electrodes which use a metal fiber substrate of high porosity of 95% in the place of the aforementioned substrate and permit required loading of the nickel hydroxide powder to be accomplished in one treatment and, do away with the repetitions of the treatment have been approaching the level of practical use.

The pasted nickel electrode is produced, as disclosed in Japanese Patent Application Disclosure SHO 61(1986)-138,458, by preparing an active material powder from an aqueous nickel nitrate solution and an aqueous sodium hydroxide solution, adding to the active material a CoO additive to form an electroconductive network in the active material, imparting the consistency of paste to the resultant mixture by addition thereto of a viscous liquid having carboxymethyl cellulose dissolved in water, and loading the pasty mix into a fiber substrate. This nickel electrode is fairly less expensive than the sintered electrode and possesses as high an energy density as 500 mAh/cc.

In consequence of the steady trend of portable electronic devices toward reduction of weight in recent years, the market needs are growing for electrodes of the class possessing a high energy level approximating 600 mAh/cc. To meet the needs, there is growing necessity for imparting high density to the nickel hydroxide powder itself because the porosity of the substrate has its own limit.

Nickel hydroxide powder of high density has found popular utility as part of the raw material for parkerizing steel sheets. This nickel hydroxide powder is produced by the method which comprises dissolving nickel nitrate or nickel sulfate in a weakly basic aqueous ammonia solution thereby giving rise to tetra-ammine nickel (II) complex ion in a stable state and adding to the resultant solution an aqueous sodium hydroxide solution thereby inducing deposition of nickel hydroxide so gradually as to preclude growth of voids in the particles being deposited. The use of the produced powder in its unmodified form as

part of the active material for batteries, however, entails several drawbacks.

For example, the charge-discharge reaction of the nickel hydroxide electrode proceeds because of free passage of protons (H^+) within the nickel hydroxide crystals. When the nickel hydroxide powder gains in density, the compactness of the crystals thereof is heightened so much as to restrict the freedom of passage of protons within the crystals and the specific surface area of the powder is decreased so much as to increase the current density, with the inevitable result that the high oxide, γ -NiOOH, which causes impairment of discharge and life characteristics as manifested in stepped discharge and swelled electrode, will be suffered to occur in a large amount.

The swelling of nickel electrode due to formation of γ -NiOOH is caused by conversion of high density β -NiOOH to low density γ -NiOOH, as disclosed in J. Appl. Electrochem., 16,403 (1986) and J. Power Source, 12,219 (1984)

SUMMARY OF THE INVENTION

An object of this invention is to provide a nickel electrode which precludes the formation of the higher oxide, γ -NiOOH, ensures enhanced utility of the active material, and enjoys high energy density and long service life and an alkaline battery using the nickel electrode.

The other objects and characteristics of the present invention will become apparent to those skilled in the art as the disclosure is made in the following description of preferred embodiments as illustrated in the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a model showing the reaction mechanism of CoO additive.

Fig. 2 is a diagram showing the relation between the specific surface area and the pore volume of nickel hydroxide particles.

Fig. 3 is a diagram showing the curves of pore size distribution obtained of the conventional nickel hydroxide powder and the high-density nickel hydroxide powder of the present invention.

Fig. 4 is a diagram showing the relation between the standing condition and the ratio of utilization of active material.

Fig. 5 is a photograph of cobalt E.P.M.A. after solution and deposition of a CoO additive.

Fig. 6 is a diagram showing the relation between the kind of nickel hydroxide and the ratio of utilization of active material.

Fig. 7 is a diagram showing the relation between the amount of CoO added, the ratio of utilization of active material, and the energy density per unit volume of electrode.

Fig. 8 is a diagram showing the relation between the composition of active material and the amount of γ -NiOOH formed.

Fig. 9 is a diagram comparing an electrode suffering heavy formation of γ -NiOOH and the electrode of this invention in terms of discharge voltage characteristic.

Fig. 10 is a diagram showing the relation between the active material composition, the charge-discharge temperature and the ratio of utilization of active material.

Fig. 11 is a diagram showing the relation between various kinds of cobalt compound additives and the ratio of utilization of active material.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

This invention specifically is directed to a pasted nickel electrode using a porous alkali-proof metal fiber substrate as a current collector and a nickel hydroxide powder as a principal component of active material and intended for use in an alkaline battery, which nickel electrode is characterized by the fact that the nickel hydroxide powder possesses a pore radius in the range of 15 to 30 Å, a total pore volume of not more than 0.05 ml/g, and a specific surface area in the range of 15 to 30 m²/g and to an alkaline battery using the nickel electrode.

The aforementioned nickel electrode for an alkaline battery is such that the nickel hydroxide active material thereof contains 2 to 7% by weight of cadmium and this cadmium is present in the state of solid solution in the crystals of nickel hydroxide.

The alkaline battery of this invention using the aforementioned nickel electrode is characterized by a process of manufacture which comprises incorporating the nickel electrode in a battery proper without entailing any forming, injecting an electrolyte in the battery properly, allowing the contents of the battery proper to stand for not less than one day thereby allowing the cobalt compound in the electrolyte to be thoroughly dissolved and deposited, and thereafter subjecting the battery to first charging.

When a high-density nickel hydroxide powder produced with the minimized inner pore volume suffers heavy occurrence of the higher oxide, γ -NiOOH. When a different metal ion, metal ions of a different species, particularly cadmium ions are distributed in the crystals of nickel hydroxide, the ions function to deform the crystals, add to the freedom of passage of protons, improve the ratio of utilization, and diminish the formation of γ -NiOOH.

When a cobalt compound additive is dissolved outside the crystals of nickel hydroxide to establish connection between the current collector and the nickel hydroxide particles by virtue of the reaction, $\text{HCoO}_2^- \rightarrow \beta\text{-Co(OH)}_2$, before the battery is charged, the cobalt compound is converted into cobalt oxyhydroxide of high conductivity by virtue of the reaction, $\beta\text{-Co(OH)}_2 \rightarrow \text{CoOOH}$, to smoothen the flow of electrons between the nickel fibers of the current collector and the nickel hydroxide particles and increase the ratio of utilization of the active material. The mechanism of the reactions mentioned above is depicted in model in Fig. 1.

Example:

Now, the present invention will be described in detail below with reference to working examples.

In an aqueous solution of nickel nitrate containing a small amount of cadmium nitrate, ammine complex ions of nickel and cadmium were formed by addition of ammonium nitrate to the aqueous solution. The resultant solution and an aqueous sodium hydroxide solution added dropwise thereto were vigorously stirred to induce decomposition of the complex ions and gradual deposition and growth of nickel hydroxide particles having cadmium contained in the form of solid solution therein. In the conventional high-concentration alkali solution having a pH value exceeding 14, nickel hydroxide particles are deposited randomly and their pore volume is large. To avoid the trouble, it is necessary to lower the alkali concentration to the order of pH 10 to 12 and effect the deposition gradually at a temperature in the range of 20 to 90°C. By the regulation of pH and temperature, nickel hydroxide particles could be produced with widely varied specific surface area and pore volume. The results are shown in Fig. 2. In the diagram, A, B, C, D, and E represent the results of samples formed solely of nickel hydroxide and F those of a sample formed of nickel hydroxide containing cadmium in the form of solid solution and G those of a sample of the conventional method formed solely of nickel hydroxide.

Between the specific surface area and the pore volume, there exists a correlation such that the pore volume in the particles tends to increase with the increasing specific surface area. It may be safely concluded that a high-density active material of small pore volume is naturally destined to possess a small specific surface area.

In accordance with the method heretofore known widely in the art, nickel hydroxide particles of specific surface area of about 70 m²/g were produced by adding dropwise an aqueous nickel nitrate solution of an aqueous alkali solution of high concentration of pH 14.5 at 90°C. The pore size distribution of the nickel hydroxide particles is shown by the curve G in Fig. 3 and that of the aforementioned high-density active material F by the curve F in the same diagram. In the particles G produced by the conventional method, pores having radii in a wide range of 15 to 100 Å occur in a large amount and randomly so that the total volume of the pores is 0.15 ml/g, a value equaling 30 to 40% of the total volume of particles (0.41 ml/g), indicating that the particles had fairly large voids. In the case of the particles of F, the pore volume was only 0.04 ml/g, a value roughly equaling one fourth of the pore volume of the particles of G. The results indicate that the particles F had a density 20 to 30% higher than that of the particles of G. The data clearly indicate that for the particles of active material to possess high density, they must possess as small specific surface area and pore volume as possible.

In a varying nickel hydroxide powder mentioned above, a small amount of a varying cobalt compound such as CoO, $\alpha\text{-Co(OH)}_2$, $\beta\text{-Co(OH)}_2$, or cobalt acetate which, on dissolution in an alkaline electrolyte, given rise to a Co(II) complex ion, was added and thereafter an aqueous 1% carboxymethyl cellulose solution was added to produce a flowable paste liquid. A nickel electrode was obtained by loading a prescribed amount

of the paste liquid on an alkali-proof fiber substrate such as, for example a nickel fiber substrate, possessing a porosity of 95%, drying the loaded electrode, and press molding the dried electrode.

For the purpose of finding the ratio of utilization of active material and the ratio of formation of γ -NiOOH by the charge-discharge reaction, a battery was assembled by opposing a cadmium electrode to the aforementioned nickel electrode as a counter electrode inside a battery housing through the medium of a nonwoven polypropylene fabric separator and then injecting a potassium hydroxide electrolyte in the battery housing. After the injection of the electrolyte, the cobalt compound as an additive was dissolved therein in a corrosive potential and left standing under varying conditions to establish connection between the nickel hydroxide particles.

The relation between the standing conditions and the ratio of utilization of active material found by using CoO as an additive and a nickel hydroxide powder possessing a specific surface area of $70 \text{ m}^2/\text{g}$ is shown in Fig. 4. The data show that the standing conditions which constitute an important process for the formation of an electroconductive network are such that the ratio of utilization of active material is heightened and the period required is shortened in proportion as the electrolyte concentration and the standing temperature are increased and the dissolved CoO amount functions effectively. It is further noted from the photograph of cobalt E.P.M.A. obtain after the solution and deposition of the additive (Fig. 5) that the proportional relation mentioned above is ascribable to the uniformity of dispersion (thoroughness of the formation of network) according to the solution and deposition of the additive.

The relation between the kind of nickel hydroxide and the ratio of utilization of active material under proper standing conditions is shown in Fig. 6.

In the composition of active material which is formed solely of nickel hydroxide, there exists a proportional relation. This fact indicates that for the purpose of enabling the active material to be utilized in a high ratio, the active material must possess a large specific surface area. It naturally implies that the desirability of the active material increases with the increasing pore volume and the decreasing density thereof. The powder F which contains a small amount of cadmium in the crystals of nickel hydroxide, however, exhibited as high a ratio of utilization as the conventional powder G in spite of a small specific surface area.

Table 1

	G	F
Amount of CoO added	10 wt%	10 wt%
Energy density per unit volume of electrode sheet	504 mAh/cc	590 mAh/cc
Ratio of utilization of active material	95%	95%

The energy density per unit volume of electrode sheet was 504 mAh/cc for the conventional powder G and 590 mAh/cc for the high-density powder F as shown in Table 1, indicating that the value for F was 15 to 20% higher than that for G.

From these results and for the reason given above, it is safely concluded that in a substrate sheet of a fixed volume, the high-density powder can be loaded in a larger amount than the conventional powder.

For the high-density powder of active material to possess an energy density on the order of 600 mAh/cc as demanded in the market, the pore volume of the powder must be not more than 0.05 ml/g and the specific surface area thereof which has a proportional relation with the pore volume must fall in the range of 15 to $30 \text{ m}^2/\text{g}$. This effect of the addition of cadmium may be logically explained by a postulate that while the decrease of the specific surface area results in a reduction in the openings for passage of reaction species protons from the electrolyte, the deformation imparted to the nickel hydroxide crystals smoothens the passage of protons in the solid phase so much as to make up for the aforementioned decrease in the openings.

The ratio of utilization of active material means the amount of passage of protons and it is controlled by the two factors, i.e. the specific surface area of the particles and the rate of diffusion inside the crystals (solid phase). It is considered that the ratio of utilization is controlled by the specific surface area where the crystals are now varied and by the internal deformation where the crystals are varied.

For the active material to react, smooth passage of electrons from the current collector to the surface of the particles of active material is an essential requirement. To the smooth passage of electrons, the presence of an electroconductive network of CoOOH particles in a free state (existing in the surface of the CoOOH particles without forming a solid solution with nickel hydroxide) is indispensable.

As regards the CoO additive which is destined to form the network, Fig. 7 shows the relation between the amount of CoO added, the ratio of utilization of active material, and the energy density per unit volume of the electrode sheet. As the amount of the CoO added is increased, so the ratio of utilization of active material is heightened to be converged in the vicinity of 100%. Since the additive itself merely contributes to the electroconductivity and takes no part actually in discharge, the actual energy density of the electrode sheet tends to decline from the vicinity of 15%. Fig. 4 depicts three-dimensionally the relation of the composition of active material and the amount of formation of γ -NiOOH. When the electrode sheet is charged with a high current density of 1C and the electrode sheet is analyzed with X-ray at the end of the charging, it is found from the relation between the kind of powder and the amount of γ -NiOOH formed that the addition of cadmium in the form of solid solution to the crystals of nickel hydroxide causes the formed amount of γ -NiOOH to decrease in reverse proportion to the amount of cadmium added. Fig. 9 compares the high-density powder A containing no cadmium and the cadmium-containing high-density powder F of this invention in terms of discharge voltage characteristic. In the case of the high-density powder A containing no cadmium, the discharge voltage shows a stepped characteristic because of heavy formation of γ -NiOOH. From Fig. 8, it is clearly noted that the addition of cadmium began to manifest its effect in preventing the formation of γ -NiOOH when the amount of cadmium reached 2% and brought about complete extinction of γ -NiOOH when the amount reached 7%.

This effect of cadmium is not affected at all by the co-existence of other element such as, for example, cobalt in the form of solid solution. Cobalt is found to exhibit a behavior similar, though only slightly, to cadmium. When the product at the end of the charging, which is trivalent β -BiOOH is perfectly reduced to bivalent β -Ni(OH)₂, it indicates a theoretical capacity = 0.29 Ah/g (amount of active material).

When the electrode indicates the above theoretical capacity, it is customary to regard the active material utilization as 100%. As for the nickel hydroxide electrode, such the electrode as having a heightened active material utilization can not always be considered to be an excellent electrode. For example, as disclosed in J. Power Sources, 12,219, (1984), there have sometimes been the electrodes having the active material utilization ratio exceeding 100%. Such high active material utilization ratio is caused by a formation of tetra-valent higher oxide, γ -NiOOH, wherein γ -NiOOH tends to be formed by the charging at a low temperature. For example, the particles G composed of only nickel hydroxide and having a large specific surface area, which are produced by the conventional method, indicate a high active material utilization ratio of 120% at a temperature of 0°C, as shown in Figure 10. However, in case of the particles G, the volumetric change takes place vigorously and due to the formation of γ -NiOOH the electrode becomes swollen so that the life of the electrode may be greatly impaired. Accordingly, the crystal form of the active material at the end of charge is required to be a trivalent β -NiOOH. In this sense it is not preferable that the ratio of utilization of active material exceeds 100%. Therefore, the electrode in which the formation of γ -NiOOH is suppressed in any conditions and the ratio of utilization of the active material is maintained in the vicinity of 100% can be defined as an excellent electrode. As shown in Figure 10, in the high-density powder F containing 5% of cadmium in the form of solid solution the ratio of utilization of the active material in the vicinity of 100% is maintained even at a low temperature. The high-density powder containing 5% of cadmium and 3% of cobalt in the form of solid solution is found to improve the high-temperature performance as disclosed in Japanese Patent Application Disclosure SHO 59- (1984) - 224,062 and to provide a little volumetric change.

With respect to the other additives cited above as useful for the formation of a network of CoOOH, the results similarly obtained were as shown in Fig. 11. In the decreasing order of the ratio of utilization of active material, these additives fell in this row : CoO > α -Co(OH)₂ > β -Co(OH)₂. This order of the ratio of utilization may be ascribed in the magnitude of solubility in the electrolyte. In the case of β -Co(OH)₂, after the injection of the electrolyte, this additive is liable to be oxidized with the dissolved oxygen to form a brown product of oxidation, Co(OH)₃, of poor solubility. In contrast, α -Co(OH)₂ is less liable to form Co(OH)₃ because it has to go through the path of α -Co(OH)₂ \rightarrow β -Co(OH)₂. CoO may well be called the most desirable additive because it does not form Co(OH)₃ at all.

More definitely, CoO which is desirable from the viewpoint of dissolving rate is produced by heating β -Co(OH)₂ at a temperature of 200°C to 800°C in an inert atmosphere. The pasted electrode loaded with the powder in which nickel hydroxide is dipped in HCoO₂⁻ ions to form a cobalt hydroxide layer on the surface was inferior to the electrode formed by mixing CoO powders in respect of the ratio of utilization of active material and was as much as the electrode formed by mixing β -Co(OH)₂ powders in the ratio of magnetization of active material. As for the pasted electrode loaded with the powder in which a conductive CoOOH layer is formed on the surface of nickel oxyhydroxide (the powder of which obtained by removing nickel fiber which is a current collector from the electrode formed by mixing CoO powders after charging and discharging the electrode), the ratio of utilization of active material was inferior. This teaches that it is

indispensably required to form a conductive network (CoOOH) of active material and current collector in the produced electrode and that the formation of the conductive network in advance on the surface of the active material provides an insufficient effect. Therefore, the nickel electrode containing CoO powder of the invention is produced by incorporating the nickel electrode in a battery housing without forming, injecting an electrolyte into the battery housing, allowing the electrode and the electrolyte to stand and effecting solution and redeposition of the CoO powder in the electrolyte. The electrode produced by the invention with using the CoO additive can accomplish a theoretical ratio of utilization of active material without using a conductive additive so that it can be adopted to the sealed nickel-cadmium battery. The working examples have been described above as using a substrate of sintered metal fibers. Of course, this invention does not discriminate the nickel electrode and the alkaline battery on account of the particular type of the substrate.

The embodiments described are intended to be purely illustrative, not limitative, of the invention and persons of ordinary skill in the art, therefore, are enabled to make variations and modifications thereof without departing from the spirit and scope of the invention.

As described above, this invention provides a nickel electrode which precludes formation of the higher oxide, γ -NiOOH, permits, an improvement in the ratio of utilization of active material, and enjoys a high energy density and a long service life. Thus, this invention contributes to economy to a very large extent.

Claims

1. A nickel electrode using a porous alkali-proof metal fibre substrate as a current collector and a nickel hydroxide powder as a principal component of active material, wherein the nickel hydroxide powder possesses a pore radius in the range of 15 to 30 Å, a total pore volume of not more than 0.05 ml/g, and a specific surface area in the range of 15 to 30 m²/g.
2. An electrode according to claim 1, wherein the nickel hydroxide contains 2 to 7% by weight of cadmium, the cadmium being present in the form of solid solution in the crystals of the nickel hydroxide.
3. An electrode according to claim 2, wherein a cobalt compound capable of forming a cobalt complex ion by dissolving in an alkaline electrolyte and the cobalt hydroxide after depositing is in a free form on the particles of the active material and is not in the form of solid solution with the active material.
4. An electrode according to claim 2, wherein a small amount of cobalt is present in the form of solid solution besides cadmium.
5. An electrode according to any one of claims 1 to 4, wherein the conductivity between the current collector and the active material is retained by a cobalt oxyhydroxide (CoOOH) and the nickel electrode does not contain a conductive additive such as nickel powder or graphite powder.
6. An alkaline battery incorporating a nickel electrode according to any one of claims 1 to 5.
7. A method for making an alkaline battery incorporating a nickel electrode according to any one of claims 1 to 5, which comprises incorporating the nickel electrode in a battery housing without forming, injecting an electrolyte into the battery housing, allowing the electrode and the electrolyte to stand for at least one day thereby effecting thorough solution and redeposition of the cobalt compound in the electrolyte, and thereafter subjecting the resultant complete battery to first charging.

Fig. 1




Fig. 2






Fig. 3





B.E.T Area	Total Pore Volume
m ² /g	ml/g
G 69.95	0.15
F 20.39	0.04

Fig.4



Effect of standing conditions before 1st
charging on active material utilization.

Fig. 5



(A): Utilization : 101 %

(B): Utilization : 84 %

E.P.M.A. of cobalt

(A); After standing for 3 days at 40°C.

(B); After standing for 1 day at 20°C.

Fig. 6




Fig. 7




Fig. 9





Fig. 8





Europäisches Patentamt
European Patent Office
Office européen des brevets

Publication number:

**0 337 029
A3**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 88304830.8

(51) Int. Cl.⁵: **H01M 4/42 , H01M 4/32 ,
H01M 10/30**

(22) Date of filing: 27.05.88

(30) Priority: 11.04.88 JP 88416/88

(43) Date of publication of application:
18.10.89 Bulletin 89/42

(84) Designated Contracting States:
DE FR GB

(88) Date of deferred publication of the search report:
18.04.90 Bulletin 90/16

(71) Applicant: **YUASA BATTERY COMPANY
LIMITED**
6-6, Johsai-cho
Takatsuki-City Osaka Prefecture(JP)

(72) Inventor: **Oshitani, Masahiko**
**Yuasa Battery Company Limited 6-6,
Johsai-cho**
Takatsuki City Osaka Prefecture(JP)
Inventor: **Yufu, Hiroshi**
**Yuasa Battery Company Limited 6-6,
Johsai-cho**
Takatsuki City Osaka Prefecture(JP)

(74) Representative: **Hartley, David et al**
Withers & Rogers 4 Dyer's Buildings Holborn
London, EC1N 2JT(GB)

(54) **Nickel electrode for alkaline battery and battery using said nickel electrode.**

(57) A nickel electrode using a porous alkali-proof metal fiber substrate as a current collector and a nickel hydroxide powder as a principal component of active material is precluded from formation of the higher oxide, γ -NiOOH, improved in the ratio of utilization of the active material, and enabled to enjoy high energy density and long service life when the nickel hydroxide powder employed therein is of a specific type possessing a pore radius in the range of 15 to 30 Å, a total pore volume of not more than 0.05 ml/g. and a specific surface area in the range of 15 to 30 m²/g. An alkaline battery is also provided by the invention which uses the nickel electrode described above.

EP 0 337 029 A3



DOCUMENTS CONSIDERED TO BE RELEVANT			EP 88304830.8
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	<u>GB - A - 2 060 241</u> (LUCAS) * Abstract *	1	H 01 M 4/42 H 01 M 4/32 H 01 M 10/30
A	<u>US - A - 4 481 128</u> (JACKOVITZ et al.) * Claims *	1, 7	
D, A	<u>US - A - 4 364 422</u> (BROWN et al.) * Abstract *	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			H 01 M
The present search report has been drawn up for all claims			
Place of search VIENNA		Date of completion of the search 12-02-1990	Examiner LUX
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	